

Linroc Elite

Linroc Elite is a high-performance hybrid system which combines the versatility of tapered EPS with the thermal efficiency of flat PIR insulation. Available in an infinite range of falls and able to achieve the highest U values required.

Compatible with virtually any membrane system by changing the PIR facing to suit.

Thermal Performance

U-values are calculated for each scheme designed to ensure the required figures are achieved. Contact our technical department for further information.

Installation

Must be installed in accordance with manufacturer's recommendations. Contact our technical department for further information.

Features

- Ozone Depletion Potential of zero
- CFC, HFC and HCFC free
- Global Warming Potential <5
- BRE Green Guide A/A+ generic rating
- 100% recyclable (EPS)
- Easy handling and installation

Technical Info	EPS	PIR - Tissue Face PIR - Bitumen Face	PIR - Foil Face	Stonewool
Board Size	1200 x 1200mm	1200 x 1200mm	1200 x 1200mm	1200 x 1000mm
	1200 x 600mm	1200 x 600mm	2400 x 1200mm	
Thermal Conductivity	0.031-0.035 W/mK	0.024-0.027 W/mK	0.022 W/mK	0.039W/mK
Thickness	20-600mm	25-160mm	25-160mm	30-185mm
Falls	1:240 upwards	N/A	N/A	N/A
Compressive Strength	EPS150 - 150kPa	150kPa	150kPa	80kPa
@ 10% compression	EPS200 - 200kPa			
Fixing	Adhered - non-solvent	Adhered - non-solvent	Mechanical - thermally	Adhered -non-solvent
	PU adhesive	PU adhesive	broken fasteners	PU adhesive
	Mechanical - thermally	Mechanical - thermally	Ballasted	Mechanical - thermally
	broken fasteners	broken fasteners		broken fasteners
	Ballasted	Ballasted		Ballasted
Reaction to Fire	Class E	Class E	Class E	Class A1/A2

The manufacturer reserves the right to alter these products. All data was produced under controlled test conditions. No warranty is implied or given as to the performance of these products in any variation from test conditions.

Units 29A/B, Shrivenham 100 Business Park, Majors Road, Watchfield SN6 8TZ Tel: 01793 764 000 Email: info@linroc.co.uk